K-8010P1

COVERED ELECTRODE

FOR 560MPA GRADE STEEL

KISWEL


■ Description

- Covering is high cellulose type for vertical down position welding of pipe
- This electrode is characterized by deeply penetrating, forceful, spray type arc
- Readily removable, thin friable slag
- Good mechanical properties and the X-Ray soundness
- Stables arc performance in almost welding current

■ Classification

- AWS A5.5 : E8010-P1
- EN ISO 2560-A : E 46 3 1Ni C 25
- EN ISO 2560-B : E 55 10-P1 A

■ Welding Position




Specially

■ Base Materials

Industry	Steel Grades	Type
Pipe	API 5LX	X56, X60, X65, X70

■ All Weld Metal Test Specimen



Base metal	A36
Size	4.0*350mm
Polarity / Current	DC+ / 140~145A
Welding Position	PA / 1G
Heat Input	12.2~13.9 kJ/cm

■ Typical Mechanical Properties of Weld Metal

	Y.S (MPa)	T.S (MPa)	El. (%)	I.V (J) (J @ Temp.)	PWHT	Remark
AWS Spec.	≥460	≥550	≥19	≥27 @ -30℃	A.W	1G
K-8010P1	550	630	24	50 @ -30℃	A.W	

■ Typical Chemical Composition of Weld Metal (%)

	C	Si	Mn	P	S	Ni	Mo
AWS Spec.	≤0.20	≤0.60	≤1.20	≤0.03	≤0.03	≤1.00	≤0.50
K-8010P1	0.15	0.23	0.62	0.013	0.005	0.55	0.01

■ Weldability

		Flat, H-Fillet	V-Up & Down
Arc	Stability	Good	Good
	Concentration	Good	Excellent
	Force	Good	Good
Slag	Fluidity	Excellent	Excellent
	Removability	Good	Good
Spatter	Quantity	Good	Good
Fume	Quantity	Good	Good
Porosity	Occurrence	Good	Good

■ Welding Efficiency

Nominal electrode efficiency (%)	Deposition efficiency (%)
85~90	55~60

1) Size : 4.0*350mm
2) Nominal electrode efficiency (%) : M_D/M_{CN} *100
3) Deposition efficiency (%) : $M_D/(M_E-M_S)$*100

* M_D : mass of deposited weld metal
* M_{CN} : nominal mass of consumed core wire
* M_E : total mass of electrodes tested
* M_S : total mass of the stub ends

■ Bead Appearance









Company S, V-Down, 4.0*350mm, DC+ 130~150A

K-8010P1

■ Packaging and Available sizes



Diameter (mm)		2.5	3.2	4.0	5.0
Length (mm)		350	350	350	350
Carton	Inner	5Kg			
	Out	20Kg (5Kg x 4EA)			
Vacuum	Inner	5Kg			
	Out	20Kg (5Kg x 4EA)			

* Identification Imprint : E8010 KISWEL

* Tip Color : None

■ Recommended Welding Parameter (DC+)

Diameter (mm)	2.5	3.2	4.0	5.0
Length (mm)	350	350	350	350
Flat, Fillet, V-Down	60~100	80~130	130~180	160~220
V-Up	50~80	80~110	90~140	120~190

■ Control Instruction

1. Storage

1) On principle covered electrodes should be in their original packaging until used. If possible the packs of electrodes should be taken out of storage in the sequence in which they were received in warehouse.
2) The covered electrodes must be stored in dry rooms to protect them against damage caused by moisture. The room must be fitted out with pallets or shelves since storage directly on the floor or against the walls is not recommended.
3) Opened packs of electrodes should also be stored in dry and, if necessary, heated rooms so that there is no likelihood of the temperature dropping below the dew point.

AWS Classification	Store Condition (Opened packs of electrode)	
	Ambient Air	Holding Oven
E8010-P1	30±10℃ Humidity max. 50%	High 12~24℃ than room temperature

2. Re-drying

1) Where electrodes have become damp it is recommended that re-drying is carried out immediately prior to welding in accordance with the temperature details specified in the following table.
2) Electrodes that have been in direct contact with water, grease or oil should not be used for welding fabrication.

Type of coating	Re-drying temp. (℃)	Re-Drying time (min)
High cellulose	No need	No need

KISWEL

The Management System of KISWEL LTD, 704, Gongdan-ro, Seongsan-gu, Changwon-si, Gyeongnam 51544, Republic of Korea, 70, Saebyeok-ro 63beon-gil, Sasang-gu, Busan 47018, Republic of Korea has been approved by Lloyd's Register Quality Assurance to : IATF 16949:2016, ISO 14001:2015, applicable to : Manufacture of solid welding wires & rods, flux cored wires, submerged arc welding wires & fluxes, stainless steel welding wires & rods and covered electrodes.
More information : www.kiswel.com

